

60mil-1.5mm LLDPE

LLDPE Smooth Geomembrane



Trump Eco's 60mil polyethylene is produced from virgin polyethylene resins. It has outstanding flexibility and elongation characteristics. 60mil Polyethylene contains approximately 97.5% polymer and 2.5% carbon black, anti-oxidants and heat stabilizers, and contains no additives, fillers or extenders. 60mil Polyethylene does not contain plasticizers which can migrate to the surface, causing premature aging. Manufactured from virgin polyethylene resins, it is designed to provide a high quality, economical Geomembrane.

TESTED PROPERTY	TEST METHOD	FREQUENCY	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Thickness (min. ave.) Thickness (lowest indiv.)	ASTM D 5199	Per roll	mil (mm)	60 (1.5) 54 (1.35)
Density	ASTM D 792, Method B	200,00 lb	g/cc, max.	0.939
Tensile Properties (both directions) Strength at Break Elongation at Break	ASTM D 6693, Type IV 2in/minute	20,000 lb	lb/in width (N/mm) % (GL=2.0in)	240(42) 800
Tear Resistance	ASTM D 1004	45,000 lb	lbs (N)	37 (165)
Puncture Resistance	ASTM D 4833	45,000 lb	lbs (N)	90 (400)
Carbon Black Content	ASTM D 4218	20,000 lb	% (range)	2-3
Carbon Black Dispersion (Category)	ASTM D 5596	45,000 lb	Only near spherical agglomerates: 10 views in Cat. 1 or 2	
Oxidative Induction Time	ASTM D 3895, 200°C, 1 atm O ₂	200,000 lb	minutes	≥140
STANDARD ROLL DIMENIONS				
Roll Width			ft (m)	19 (5.8)
Roll Length			ft (m)	164 (50)
Roll Area			ft ² (m ²)	290 (3,116)

Note: Average roll weight is 959 lbs (435 kgs).

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

Geosynthetic Tek. Since 1983

Email : dennis@ecohdpe.com

Phone: +86 158.823.141.58(WhatsApp Wechat)

Web: www.ecoHDPE.com